

Color Ribbon

Thermal Transfer Ribbon

WAX Color Range Across all Ink Types

TECHNICAL DATA SHEET

Printing receptor


papers

Vellum	● ● ●
Coated	● ● ●
Glossy coated	● ● ●


Printer settings

speed


16 ips
400 mm/s



Print resistance



energy



Color Options



Compliant with the following regulations

REACH / SVHC 1907/2006/EC

Food Contact 1935/2004/EC

Heavy metals 2011/65/EU

California Proposition 65

Halogen restrictions

Environmental performance

Manufacturing process

PET Waste 100% recovered

Solvent 91% recovered into factory energy

Electricity 43% from renewable sources

Application Fields

























Wax Resin

Thermal Transfer Ribbon
WAX RESIN FOR FLAT HEAD PRINTERS

TECHNICAL DATA SHEET


2 of 2

Product performance

 90°Barcode 	 Small characters 	 Logos 
 0°Barcode 	 2D Barcode 	 Blackness <small>*Optical Density by Reflection, measured using a densitometer.</small> 
technical resistances		
 Heat 100°C / 212°F 	 Light/Blue Wool 	 Solvents 
 Water/Submerge 	 Rubbing 	

Product physico-chemical features

product structure



PET film	Thickness: 4,5 µm
Ink	Wax Resin
Melting point	75°C/167°F
Backcoating	Silicon based
Coefficient of Friction	Kd < 0.2
Ribbon thickness	< 9 µm
The ribbon is anti static build-up treated	

Storage

storage conditions

12 months recommended

20-80 % Humidity Rate, 5-35°C (40-95°F)



ASR Universal Ltd

821-299, Roehampton Avenue,
Toronto Ontario, Canada M4P1S2



+1 437 988 7611



info@asruniversalltd.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

